



SECTION 07810

BARRIER COAT FIREPROOFING

Display hidden notes to specifier. (Don't know how? [Click Here](#))

PART 1 GENERAL

1.1 SECTION INCLUDES

- A. Barrier Coat Fireproofing.

1.2 RELATED SECTIONS

- A. Section 05120 - Structural Steel: Requirements for substrates receiving sprayed fire-resistive materials.
- B. Section 07810 - Applied Fireproofing: Requirements for and application of mineral fiber and cementitious fireproofing.
- C. Section 07820 - Board Fireproofing: Requirements for and installation of mineral-fiber board fire protection.

1.3 REFERENCES

- A. ASTM D 412 - Tensile set of Rubber and Thermoplastic Elastomers.
- B. ASTM D 522 - Standard Test Methods for Mandrel Bend Test of Attached Organic Coatings.
- C. ASTM D 661 - Standard Test Method for Evaluating Degree of Cracking of Exterior Paints.
- D. ASTM D 968 - Standard Test Methods for Abrasion Resistance of Organic Coatings by Falling Abrasive.
- E. ASTM D 1729 - ASTM D1729-96 Standard Practice for Visual Appraisal of Colors and Color Differences of Diffusely-Illuminated Opaque Materials.
- F. ASTM D 2243 - Standard Test Method for Freeze-Thaw Resistance of Water-Borne Coatings.
- G. ASTM D 2486 - Standard Test Methods for Scrub Resistance of Wall Paints.
- H. ASTM D 2794 - Standard Test Method for Resistance of Organic Coatings to the Effects of Rapid Deformation (Impact).

- I. ASTM D 3273 - Test Method for Resistance to Growth of Mold on the Surface of Interior Coatings in an Environmental Chamber.
- J. ASTM D 4214 - Standard Test Methods for Evaluating the Degree of Chalking of Exterior Paint Films.
- K. ASTM D 4541 - Standard Test Method for Pull-Off Strength of Coatings Using Portable Adhesion Testers.
- L. ASTM D 4585 - Standard Practice for Testing Water Resistance of Coatings Using Controlled Condensation.
- M. ASTM D 6904 - Standard Practice for Resistance to Wind-Driven Rain for Exterior Coatings Applied on Masonry.
- N. ASTM G 153 - Standard Practice for Operating Enclosed Carbon Arc Light Apparatus for Exposure of Nonmetallic Materials
- O. FTMS 141 M 4494 - Film Application & Test Charts - Leveling & Sagging.
- P. ASTM E 84 - Standard Test Method for Surface Burning Characteristics of Building Materials.
- Q. ASTM E 96 - Standard Test Methods for Water Vapor Transmission of Materials.
- R. ASTM E 119 - Standard Test Methods for Fire Tests of Building Construction and Materials.
- S. NFPA 286 - Standard Methods of Fire Tests for Evaluating Contribution of Wall and Ceiling Interior Finish to Room Fire Growth.
- T. UL 723 - Test for Surface Burning Characteristics of Building Materials
- U. ICC - International Urban-Wildland Interface Code.
- V. SFI 54.1 - Non-Flammable Thermal Barrier Fire Extinguishing Coatings.
- W. SWRI 99-02 - Flame spread and Flame penetration resistance according to SWRI 99-02 crawl space ignition barrier test.
- X. SSPC-SP 1 - Solvent Cleaning.
- Y. SSPC-SP 2 - Hand Tool Cleaning.
- Z. SSPC-SP 3 - Power Tool Cleaning.
- AA. SSPC-SP 6 - Commercial Blast Cleaning.

1.4 DESIGN / PERFORMANCE REQUIREMENTS

- A. Fire-Resistance Ratings: As indicated by UL Fire Resistance Directory designation.

1.5 SUBMITTALS

- A. Submit under provisions of Section 01300.
- B. Product Data: Manufacturer's data sheets on each product to be used, including:
 1. Preparation instructions and recommendations.
 2. Storage and handling requirements and recommendations.

3. Installation methods.

- C. Verification Samples: For each finish product specified, two samples, minimum size 6 inches (150 mm) square, representing actual product, color, and patterns.
- D. Certification: Obtain and submit certification by authority having jurisdiction that fireproofing products are acceptable.
- E. Installer's qualification statement indicating installer is approved by the manufacturer as an installer.
- F. Manufacturer's Certificates: Certify products meet or exceed specified requirements.

1.6 QUALITY ASSURANCE

- A. Manufacturer Qualifications: Company specializing in the manufacture of the products specified, with minimum of 5 years documented experience.
- B. Installer Qualifications: Trained and approved by manufacturer, with minimum of 3 years documented experience.
- C. Mock-Up: Provide a mock-up for evaluation of surface preparation techniques and application workmanship.
 - 1. Finish areas designated by Architect.
 - 2. Do not proceed with remaining work until workmanship, color, and sheen are approved by Architect.
 - 3. Refinish mock-up area as required to produce acceptable work.
 - 4. Accepted mock-ups shall be comparison standard for remaining Work

1.7 DELIVERY, STORAGE, AND HANDLING

- A. Store products in doors in a heated location in manufacturer's unopened packaging until ready for installation.

1.8 PROJECT CONDITIONS

- A. Maintain environmental conditions (temperature, humidity, and ventilation) within limits recommended by manufacturer for optimum results. Do not install products under environmental conditions outside manufacturer's absolute limits.
- B. Do not install when substrate temperature is less than 55 degrees F (12 degrees C) or above 95 degrees F (35 degrees C) and if relative humidity is above 60 percent, contact TPR2.com
- C. Maintain ventilation after application of fireproofing in accordance with manufacturer's recommendations.
- D. Coordinate sequence of work with other installers of work that needs to penetrate fireproofing, to avoid unnecessary damage and patching.
- E. Coordinate sequence of work with other installers of work that would obstruct access to surfaces to be fireproofed.

PART 2 PRODUCTS

2.1 MANUFACTURERS

- A. Acceptable Manufacturer: TPR² Corp. (Thermal Product Research), which is located

at: 161 Interstate Ln. ; Waterbury, CT 06705; Tel: 203-756-TPR2; Email: [request info](mailto:requestinfo); Web: www.tpr2.com

- B. Substitutions: Not permitted.
- C. Requests for substitutions will be considered in accordance with provisions of Section 01600.

2.2 MATERIALS

- A. AFES-F1 Fire Extinguishing Coating:
 - 1. Proprietary Non-flammable Coating.
 - 2. Flexible, ductile, elastomeric.
 - 3. Extinguishes liquid fires as tested in accordance with SFI 54.1.
 - 4. Maintains protective integrity in vapor fires.
 - 5. Meets weatherability requirements for exterior coating as follows:
 - a. ASTM D 522: Flexibility over conical mandrel.
 - b. ASTM D 2486: Scrub resistance.
 - c. ASTM D : Abrasion, falling sand.
 - d. ASTM D 2794: Impact resistance.
 - e. ASTM D 4541: Adhesion, pull off strength.
 - f. ASTM D 2243: Freeze thaw resistance.
 - g. ASTM G 153: Accelerated weathering - 1000 hrs, 8 hours UVA 340@60c.
 - h. ASTM D 412: Tensile, elongation properties.
 - i. ASTM D 6904: Wind driven rain.
 - j. ASTM D 3273: Mold resistance.
 - k. FTMS 141 M4494: Sag resistance.
 - l. ASTM D 4585: Moisture resistance, 100 hours.
 - m. ASTM D 1729: Color change.
 - n. ASTM D 4214: Degree of chalking.
 - o. ASTM D 661: Degree of cracking.
 - 6. Non-toxic, drain safe, water based, non-fuming.
 - 7. Suitable for Interior and Exterior surfaces.
 - 8. Sprayable with standard spray equipment.
 - 9. Flame Spread/Smoke Developed ASTM E 84 and UL 723: flame 0 smoke 0.
 - 10. Volatility/VOC: 0.
 - 11. Solvent: Water based.
 - 12. Total Dry Film Thickness: 20 to 30 mils DFT, nominal.
 - 13. No primer required.
 - 14. Color:
 - a. White.
 - b. y.
 - c. Red.
 - d. Charcoal.
 - e. Black.
 - f. Custom Color.
- B. Fireshell F10E - NFPA 286 Thermal Barrier Coating for sprayfoam:
 - 1. Non-flammable, 1-part, water based, intumescent coating.
 - 2. Expands up to 2000 percent.
 - 3. Non-toxic, drain safe, water based, non-fuming.
 - 4. For Interior application.
 - 5. Can be latex or oil base top coated.
 - 6. Approvals:
 - a. Meets NFPA 286 over open cell Foam for Walls, Foam, Attics, and Crawl Spaces.

- b. Meets NFPA 286 over closed cell Foam for Walls, Foam, Attics, and Crawl Spaces.
 - c. Meets Green Standards and Lead Paint Requirements.
 - d. Meets EPA requirements for Ultra Low VOC.
 - e. Meets ASTM E 84 and UL 723, 5 flame, 20 smoke.
 - f. Meets SCAQMD (California South Coast Air Quality Management District) requirements as a Supercompliant Coating.
7. Color:
- a. White.
 - b. Custom Color.
- C. Fireshell AFES-F1E Interior/Exterior Waterproof Thermal Barrier Coating:
1. Non-flammable, 1-part water based, intumescent coating.
 2. Flexible, ductile, elastomeric.
 3. Expands up to 2000 percent.
 4. Non-toxic, drain safe, water based, non fuming.
 5. Can be latex or oil base top coated.
 6. Suitable for Interior and Exterior surfaces.
 7. Meets weatherability requirements for exterior coating as follows:
 - a. ASTM D 522: Flexibility over conical mandrel.
 - b. ASTM D 2486: Scrub resistance.
 - c. ASTM D : Abrasion, falling sand.
 - d. ASTM D 2794: Impact resistance.
 - e. ASTM D 4541: Adhesion, pull off strength.
 - f. ASTM D 2243: Freeze thaw resistance.
 - g. ASTM G 153: Accelerated weathering - 1000 hrs, 8 hours UVA 340@60c.
 - h. ASTM D 412: Tensile, elongation properties.
 - i. ASTM D 6904: Wind driven rain.
 - j. ASTM D 3273: Mold resistance.
 - k. FTMS 141 M4494: Sag resistance.
 - l. ASTM D 4585: Moisture resistance, 100 hours.
 - m. ASTM D 1729: Color change.
 - n. ASTM D 4214: Degree of chalking.
 - o. ASTM D 661: Degree of cracking.
8. Approvals:
- a. Water Vapor Transmission: 0.5 grains/sf/hr, ASTM E 96.
 - b. Water Vapor Permeance: 0.9 perms, ASTM E 96.
 - c. Meets UL 263/ASTM E 119, 1 Hour Wall, 1/2 inch gypsum with 12 mils DFT.
 - d. Meets UL 263 ASTM E 119, 2 Hour Wall, 1/2 inch gypsum with 18 mils DFT.
 - e. Meets IBC AC12 and SWRI 99-02 Crawl space Ignition Barrier test over foam insulation with 8 mils DFT.
 - f. Meets ASTM E 119 and UL 263 coated closed cell spray foam 15 minute wall assembly test with 16 mils DFT. 16 Minute Rating.
 - g. Meets ASTM E 119 and UL 263 coated closed cell spray foam 15 minute wall assembly test with 21 mils DFT. 34 Minute Rating.
 - h. Meets ASTM E 84 and UL 723, Class A and 1/2 hour noncombustible ratings. Meets Urban Wildlife Codes.
 - i. Meets ASTM E 84 and UL 723, Class A, 15 mils DFT on cement board. Flame 0, Smoke 0.
9. Color:
- a. Light Gray.
 - b. Custom Color.

- D. Fireshell AFES-F5E Interior/Exterior Waterproof, Fire Extinguishing Barrier Coating:
1. Non-flammable, 1-part water based, intumescent coating.
 2. Extinguishes liquid based fires, blocks vapor fires from substrates.
 3. Flexible, ductile, elastomeric.
 4. Expands up to 2000 percent.
 5. Non-toxic, drain safe, water based, non fuming.
 6. Can be latex or oil base top coated.
 7. Suitable for Interior and Exterior surfaces.
 8. Meets weatherability requirements for exterior coating as follows:
 - a. ASTM D 522: Flexibility over conical mandrel.
 - b. ASTM D 2486: Scrub resistance.
 - c. ASTM D : Abrasion, falling sand.
 - d. ASTM D 2794: Impact resistance.
 - e. ASTM D 4541: Adhesion, pull off strength.
 - f. ASTM D 2243: Freeze thaw resistance.
 - g. ASTM G 153: Accelerated weathering - 1000 hrs, 8 hours UVA 340@60c.
 - h. ASTM D 412: Tensile, elongation properties.
 - i. ASTM D 6904: Wind driven rain.
 - j. ASTM D 3273: Mold resistance.
 - k. FTMS 141 M4494: Sag resistance.
 - l. ASTM D 4585: Moisture resistance, 100 hours.
 - m. ASTM D 1729: Color change.
 - n. ASTM D 4214: Degree of chalking.
 - o. ASTM D 661: Degree of cracking.
 9. Approvals:
 - a. Water Vapor Transmission: 0.5 grains/sf/hr, ASTM E 96.
 - b. Water Vapor Permeance: 0.9 perms, ASTM E 96.
 - c. Meets SFI 54.1 Non-Flammable, Thermal Barrier/Fire Extinguishing Coatings.
 - d. Meets UL 263/ASTM E 119, 1 Hour Wall, 1/2 inch gypsum with 12 mills DFT.
 - e. Meets UL 263 ASTM E 119, 2 Hour Wall, 1/2 inch gypsum with 18 mills DFT.
 - f. Meets SWRI 99-02 Crawl space Ignition Barrier test over foam insulation with 8 mils DFT.
 - g. Meets ASTM E 119 and UL 263 coated closed cell spray foam 15 minute wall assembly test with 16 mils DFT. 16 Minute Rating.
 - h. Meets ASTM E 119 and UL 263 coated closed cell spray foam 15 minute wall assembly test with 21 mils DFT. 34 Minute Rating.
 - i. Meets ASTM E 84 and UL 723, Class A and 1/2 hour noncombustible ratings. Meets Urban Wildlife Codes.
 - j. Meets ASTM E 84 and UL 723, Class A, 15 mils DFT on cement board. Flame 0, Smoke 0.
 10. Color:
 - a. Light Gray.
 - b. Black.
 - c. Custom Color.
- E. FIRESHHELL AFES-M1E Mastic:
1. Non-flammable, 1-part water based, reinforced, intumescent coating.
 2. Expands up to 2000 percent.
 3. Non-toxic, drain safe, water based, non fuming.
 4. Can be latex or oil base topcoat.
 5. Suitable for Interior and Exterior surfaces.
 6. Meets weatherability requirements for exterior coating as follows:

- a. ASTM D 522: Flexibility over conical mandrel.
- b. ASTM D 2486: Scrub resistance.
- c. ASTM D : Abrasion, falling sand.
- d. ASTM D 2794: Impact resistance.
- e. ASTM D 4541: Adhesion, pull off strength.
- f. ASTM D 2243: Freeze thaw resistance.
- g. ASTM G 153: Accelerated weathering - 1000 hrs, 8 hours UVA 340@60c.
- h. ASTM D 412: Tensile, elongation properties.
- i. ASTM D 6904: Wind driven rain.
- j. ASTM D 3273: Mold resistance.
- k. FTMS 141 M4494: Sag resistance.
- l. ASTM D 4585: Moisture resistance, 100 hours.
- m. ASTM D 1729: Color change.
- n. ASTM D 4214: Degree of chalking.
- o. ASTM D 661: Degree of cracking.

7. Approvals

- a. Water Vapor Transmission: 0.5 grains/sf/hr, ASTM E 96.
- b. Water Vapor Permeance: 0.9 perms, ASTM E 96.
- c. Meets ASTM E 119 and UL 263 Steel Beam 1 hour rating with 180 mils DFT.
- d. Meets ASTM E 162, Class A.

8. Color:

- a. y.
- b. Custom Color.

F. FIRESAFE IP-10 Interior Paint

- 1. White, Non-flammable coating.
- 2. Non-toxic, drain safe, water based, non fuming.
- 3. Interior tintable.
- 4. Topcoatable.
- 5. Meets ASTM E 84 and UL 723, Class A. 7 mils DFT on cement board. Flame 0, Smoke 0.
- 6. Color:
 - a. White.
 - b. y.
 - c. Red.
 - d. Charcoal.
 - e. Black.
 - f. Custom Color.

G. HEATSHEDDER HS-1 Interior Hardshell Intumescent Primer

- 1. White, non-flammable intumescent coating.
- 2. Hardshell barrier coating maintains integrity.
- 3. Provides oxygen starvation.
- 4. Non-toxic, drain safe, water based, no fuming.
- 5. Sprayable.
- 6. Interior - tintable.
- 7. Topcoatable.
- 8. Sprayable.
- 9. Meets ASTM E 84 and UL 723, Class A. Heatshedder 8 mils DFT, over Fireshell Ultra 8 mils DFT on plywood. Flame 0, Smoke 0.

H. HEATSHEDDER HS-2 Interior Hardshell, Fire Extinguishing, Intumescent Primer

- 1. White, non-flammable intumescent coating.
- 2. Hardshell barrier coating maintains integrity.

3. Provides oxygen starvation.
4. Non-toxic, drain safe, water based, no fuming.
5. Sprayable.
6. Interior - tintable.
7. Topcoatable.
8. Sprayable.
9. Meets ASTM E 84 and UL 723, Class A. Heatshedder 8 mils DFT, over Fireshell Ultra 8 mils DFT on plywood. Flame 0, Smoke 0.

I. STRUCTURE SAVIOUR AFES-F1EP Fireproof Intumescent Primer:

1. Non-flammable, 1-part water based, intumescent coating.
2. Expands up to 2000 percent.
3. Non-toxic, drain safe, water based, non fuming.
4. Suitable for Interior and Exterior surfaces.
5. Has stain blocking capability.
6. Meets weatherability requirements for exterior coating as follows:
 - a. ASTM D 522: Flexibility over conical mandrel.
 - b. ASTM D 2486: Scrub resistance.
 - c. ASTM D 968: Abrasion, falling sand.
 - d. ASTM D 2794: Impact resistance.
 - e. ASTM D 4541: Adhesion, pull off strength.
 - f. ASTM D 2243: Freeze thaw resistance.
 - g. ASTM G 153: Accelerated weathering -1 000 hrs, 8 hours UVA 340@60c.
 - h. ASTM D 412: Tensile, elongation properties.
 - i. ASTM D 6904: Wind driven rain.
 - j. ASTM D 3273: Mold resistance.
 - k. FTMS 141 M4494: Sag resistance.
 - l. ASTM D 4585: Moisture resistance, 100 hours.
 - m. ASTM D 1729: Color change.
 - n. ASTM D 4214: Degree of chalking.
 - o. ASTM D 661: Degree of cracking.
7. Can be latex or oil base top coated.
8. Approvals:
 - a. Meets ICC urban-wildland interface code requirements for ignition resistance over wood and lumber.
 - b. Water Vapor Transmission: 0.5 grains/sf/hr, ASTM E 96.
 - c. Water Vapor Permeance: 0.9 perms, ASTM E 96.
 - d. Meets ASTM E 84 and UL 723, Class A, 15 mils DFT on cement board. Flame 0, Smoke 0.
9. Color: Gray.

J. AFES-F4 non flammable exterior paint:

1. Proprietary Non-flammable Coating.
2. Flexible, ductile, elastomeric.
3. Maintains protective integrity in vapor fires.
4. Meets weatherability requirements for exterior coating as follows:
 - a. ASTM D 522: Flexibility over conical mandrel.
 - b. ASTM D 2486: Scrub resistance.
 - c. ASTM D : Abrasion, falling sand.
 - d. ASTM D 2794: Impact resistance.
 - e. ASTM D 4541: Adhesion, pull off strength.
 - f. ASTM D 2243: Freeze thaw resistance.
 - g. ASTM G 153: Accelerated weathering - 1000 hrs, 8 hours UVA 340@60c.
 - h. ASTM D 412: Tensile, elongation properties.

- i. ASTM D 6904: Wind driven rain.
- j. ASTM D 3273: Mold resistance.
- k. FTMS 141 M4494: Sag resistance.
- l. ASTM D 4585: Moisture resistance, 100 hours.
- m. ASTM D 1729: Color change.
- n. ASTM D 4214: Degree of chalking.
- o. ASTM D 661: Degree of cracking.
- 5. Non-toxic, drain safe, water based, non-fuming.
- 6. Suitable for Interior and Exterior surfaces.
- 7. Sprayable with standard spray equipment.
- 8. Flame Spread/Smoke Developed ASTM E 84 and UL 723: flame 0 smoke 0.
- 9. Volatility/VOC: 0.
- 10. Solvent: Water based.
- 11. Total Dry Film Thickness: 7-9 mils DFT, nominal.
- 12. Color:
 - a. White
 - b. Gray.
 - c. Red.
 - d. Charcoal.
 - e. Black.
 - f. Custom Color.

PART 3 EXECUTION

3.1 EXAMINATION

- A. Do not begin installation until substrates have been properly prepared.
- B. Verify that substrates are ready to receive barrier coat fireproofing.
- C. Ensure that all primers are compatible with the barrier coat fireproofing.
- D. Verify that items that need to penetrate the barrier coat fireproofing film are in place, including clips, hangers, supports, and sleeves.
- E. Verify that other work that would obstruct access to surfaces to be fireproofed has not been installed.
- F. Where barrier coat fireproofing is to be exposed to view as a finished surface, verify that surfaces are smooth, without voids, cracks, or projections.
- G. If substrate preparation is the responsibility of another installer, notify Architect of unsatisfactory preparation before proceeding.

3.2 PREPARATION

- A. Clean surfaces thoroughly prior to installation.
- B. Prepare surfaces using the methods recommended by the manufacturer for achieving the best result for the substrate under the project conditions.
- C. Clean surfaces of dirt, dust, grease, oil, loose material, and other matter that may affect bond of fireproofing.
- D. Clean surfaces in accordance with manufacturer's instructions and SSPC-1, SSPC-2, SSPC-3, or SSPC-6 as required to obtain substrate suitable for installation of fireproofing.

- E. Seal penetrations and open ended fireproofing terminations as required by manufacturer.
- F. Protect floors and adjacent walls and ceilings from overspray, fall-out, and dusting.

3.3 INSTALLATION

- A. Install in accordance with manufacturer's instructions.
- B. Prime all surfaces unless existing primer is suitable and undamaged and compatible with fireproofing.
- C. Install fireproofing in sufficient thickness to achieve fire rating indicated. Use as many passes as necessary to cover with a monolithic coating of uniform hardness, density, and texture.
- D. Remove fireproofing from surfaces not specifically required to be fireproofed.

3.4 FIELD QUALITY CONTROL

- A. Field inspection and testing will be performed by Owner's independent testing agency.
- B. Correct defective work and provide further inspection and testing to verify compliance, at no cost to Owner.

3.5 PROTECTION

- A. Protect installed products until completion of project.
- B. Remove excess material, overspray, droppings, and debris.
- C. Where fireproofing is subsequently cut away to facilitate installation of other work, patch fireproofing to same thickness and texture after installation of other work at no cost to Owner.
- D. Touch-up, repair or replace damaged products before Substantial Completion.

END OF SECTION